This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of the Claims:

5

- 1-25. (Canceled)
- 26. (Currently Amended) A method of separating a <u>ceramic</u> component from a metal<u>-ceramic</u> based composite, the method including the steps of increasing the size of a-at <u>least the ceramic</u> component within the metal<u>-ceramic</u> based composite by heating the metal<u>-ceramic</u> based composite and then separating of the increased sized <u>ceramic</u> component from the other components of the crushed composite to result in a metal rich fraction.
- 27. (Original) The method according to claim 26 wherein the metal based composite is heated to a temperature of between about 1500°C and about 1650°C.
- 28. (Original) The method according to claim 26 wherein the metal based composite is held at a temperature of between 1500°C and 1650°C for a time of between about 0.5 hours and about 10 hours.
- 29. (Original) The method according to claim 26 wherein the component increases in size to between about 15μm and about 100μm.

Claim 30 (Canceled)

31. (Original) The method according to claim 26 wherein the metal is titanium, yttrium or copper.

Claims 32-33 (Canceled)

- 34. (Currently Amended) The method according to claim 26 wherein the metal based composite is a metal-ceramic composite where has a major component and the major component makes up greater than about 50% of the composite.
- 35. (Currently Amended) The method according to claim 26 wherein the materials or phases that make up the metal-ceramic based composite includes metallic phases, intermetallic phases, oxides, nitrides, carbides or silicates.

- 36. (Currently Amended) The method according to claim 26-35 wherein the materials or phases that make up the metal based composition include metallic phases, intermetallic phases and oxides that include Ti(Al,O), Ti₃Al(O) and TiAl(O) and Al₂O₃.
- 37. (Currently Amended) The method according to claim 26 wherein the <u>ceramic</u> component that increases in size in the <u>metal based composite</u> is Al₂O₃.

Claims 38-46 (Canceled)

- 47. (New) The method according to claim 37 wherein the mean particle size of the Al₂O₃ is increased by the heat treatment which brings about coarsening of the Al₂O₃ particles.
- 48. (New) The method according to claim 26 wherein the step of crushing the metal-ceramic based composite following heat treatment results in the formation of a powder and also a decrease in the size of a component in comparison to other components.
- 49. (New) The method according to claim 48 wherein the metal-based ceramic composite is crushed and milled following heat treatment to form a powder and to decrease the size of a component in comparison to other components.
- 50. (New) The method according to claim 49 wherein the crushing or crushing and milling occurs in an inert environment such as under argon or a vacuum.
- 51. (New) The method according to claim 49 wherein the crushing time or crushing and milling time is limited to minimize reduction of the increased size of the component.
- 52. (New) The method according to claim 48 wherein the powder is mixed with surfactant and water to produce a suspension for separation.
- 53. (New) The method according to claim 26 wherein separation of the components is achieved by sedimentation, electrophoresis, electrostatic methods, chemical leaching, or the like.
- 54. (New) The method according to claim 26 wherein the method produces a metal rich fraction in powder form having a volume fraction of the metal component greater than about 70%.

Application No. 10/522,054 Amendment Dated April 9, 2008 Reply to Office Action of January 15, 2008

- 55. (New) The method according to claim 54 wherein the volume fraction is greater than about 90%.
- 56. (New) The method according to claim 54 wherein the metal rich fraction collected following separation is reacted with a reducing agent.
- 57. (New) The method according to claim 54 wherein the oxygen content of the metal rich fraction is less than about 1.5 atomic %.